

TECHNICAL SHEET



Article: **B0184 MORRISON**
 Norm: **UNI EN ISO 20345:2011**
 Safety Class: **S3 SRC**

Footwear height: **Mod. B, H 125 mm (≥ 113 mm, Rif. EN 20345-5.2.2)**

Width: **11**

Construction: **STROBEL; PU SOLE**

Cleaning and maintenance: Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.

Suggested environments: **Agriculture, mechanics, building, shipbuilding, handcraft.**

Entire footwear: components				
Component	Description	Value	Norm Requirements	EN 20345
Steel toe-cap	Impact resistance(200 J)			
	• Free height after impact	14,5 mm	≥ 14 mm	5.3.2.3
	Compression resistance (15 kN)			
	• Free height after compression	14,5 mm	≥ 14 mm	5.3.2.4
Sole (SRC)	Slip resistance			
	• SRA – Sole (entire sole)	0,41	$\geq 0,32$	5.3.5.4
	• SRA – Heel (Angle of 7°)	0,37	$\geq 0,28$	5.3.5.4
	• SRB – Sole (entire sole)	0,18	$\geq 0,18$	5.3.5.4
	• SRB – Heel (Angle of 7°)	0,15	$\geq 0,13$	5.3.5.4
Steel sheet (P)	Puncture resistance	No perforation	≥ 1100 N	6.2.1.1.2
Footbed (A)	Antistatic properties			
	• Electrical resistance	dry $10 \times 10^8 \Omega$ humid $8,82 \times 10^8 \Omega$	$\geq 10^5 \Omega$, $\leq 10^9 \Omega$ $\geq 10^5 \Omega$, $\leq 10^9 \Omega$	6.2.2.2 6.2.2.2
Sole/Upper	Thermal insulation			
	Heat (HI)	Insole temperature increase	$\leq 22^\circ\text{C}$	6.2.3.1
Cold (CI)	Insole temperature decrease	N/A	$\leq 10^\circ\text{C}$	6.2.3.2
Heel (E)	Shock-absorption in the heel region	36 J	≥ 20 J	6.2.4
(WR)	Water resistance (Water absorption)	N/A	$\leq 3 \text{ cm}^2$	6.2.5
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6

Upper				
Component	Description	Value	Norm Requirements	EN 20345
Water-resistant grain leather	Tear resistance	190 N	≥ 120 N	5.4.3
	Traction resistance	N/A	$\geq 15 \text{ N/mm}^2$	5.4.4
	Water steam permeability	$1,8 \text{ mg/cm}^2 \text{ h}$	$\geq 0,8 \text{ mg/cm}^2 \text{ h}$	5.4.6
	pH value	4,35	$\geq 3,2$	5.4.7
	Chromium VI content	Not detected	Not detectable	5.4.9
	Water passed	0 g	$\leq 0,2 \text{ g}$	6.3
	Water absorption	12 %	$\leq 30\%$	6.3

Lining				
Component	Description	Value	Norm Requirements	EN 20345
3D hi-tech Fabric	Tear resistance	30 N	≥ 15 N	5.5.1
	Abrasion resistance	- Dry : the surface shows no holes - humid: the surface shows no holes	No holes till 51.200 cycles	5.5.2
			No holes till 25.600 cycles	5.5.2
	Water steam permeability	7,2 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	pH value	N/A	Not detectable	5.5.4
	Chromium VI content	N/A	Not detectable	5.5.5

Insole				
Component	Description	Value	Norm Requirements	EN 20345
TNT	Thickness	3,5 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	109 mg/cm ²	≥ 70 mg/cm ²	5.7.3
	Water release	100 %	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI content	N/A	Not detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm Requirements	EN 20345
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm ²	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25600 cycles Humid no holes till 12800 cycles	5.7.4.2
	Chromium VI content	N/A	Not detectable	5.7.5

Sole				
Component	Description	Value	Norm Requirements	EN 20345
PU Monodensity sole	Sole thickness without profiles	10 mm	≥ 4 mm	5.8.1.1
	Profile height	3 mm	≥ 2,5 mm	5.8.1.3
	Tear resistance	6,0 kN/m	≥ 5 kN/m	5.8.2
	Abrasion resistance			
	• relative volume loss	186 mm ³	≤ 250 mm ³	5.8.3
	Flexion resistance			
	• Notches increase after 30.000 cycles	3 mm	≤ 4 mm	5.8.4
	• Hydrolysis	1 mm	≤ 6 mm	5.8.5
	• Notches increase after 150.00 cycles		≥ 4 N/mm;	5.8.6
	Detachment Midsole/Outsole	N/A	(*) ≥ 3 N/mm with sole ripping	
	(HRO) Contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1
	(FO) Fuel resistance (volume changes)	-0,1 %	≤ 12%	6.4.2

Date: 02/04/2013

Issued by: Resp.Techn.Eng. A.DITERLIZZI

Signature

